

Product Name: 6" Stud
Description: 600S162-54

Physical Properties

Web Depth (in)	6.00	Gauge	16
Flange Width (in)	1.625	Mils	54
Return Lip (in)	0.500	Design Thickness (in)	0.0566
Standard Coating	CP60	Minimum Thickness (in)	0.0538
Available Coating *	CP90	Yield Stress Fy (ksi)	50
Weight (lb/ft)	1.890	Ultimate, Fu (ksi)	65

Section Properties

Cross Sectional Area (A)	0.556 in ²
Moment of Inertia (Ix)	2.861 in ⁴
Radius of Gyration (Rx)	2.268 in
Gross Moment of Inertia (Iy)	0.180 in ⁴
Gross Radius of Gyration (Ry)	0.570 in

Effective Section Properties

Moment of Inertia for Deflection (Ixe)	2.860 in ⁴
Section Modulus (Sxe)	0.916 in ³
Allowable Bending Moment (Ma)	30.33 in-k

Torsional Properties

St. Venant Torsion Constant (Jx1000)	0.594 in ⁴
Warping Constant (Cw)	1.337 in ⁶
Distance from Shear Center to Neutral Axis (Xo)	-1.049 in
Radii of Gyration (Ro)	2.562 in
Torsional Flexural Constant (Beta)	0.832

*By request



MANUFACTURING Codes & Standards

NASPEC AISI S100-07 IBC 2009 2012 Compliant
 Coated in accordance to ASTM A1003 & A653
 Meets or exceeds ASTM C955 & AISI S200
 Code Evaluation Report ICC-ESR #3957

GREEN Benefits & LEED Data:

LEED Credit MR 2 - Construction Waste Mgmt - 1-2 Points
 LEED Credit MR 4 - Recycled Credit - 1-2 Points
 LEED Credit MR 5 - Regional Materials - 1-2 Points
 CRACO products are 100% recyclable
 Contact Technical Services for more information